

ADHESIVE FORMULATIONS E BOOKS



**ADHESIVE
PRODUCTS
FORMULATIONS
E – BOOKS**

ADHESIVE FORMULATIONS E BOOKS



Allrights of this publications belongs to

SOLVERCHEMBOOKS

ADHESIVE FORMULATIONS E BOOKS



CEMENT BASED
STONE AND CONCRETE
ADHESIVE
FORMULATIONS
E – BOOKS

CONTENT

CEMENT BASED STONE AND CONCRETE ADHESIVES FORMULATIONS AND MANUFACTURING PROCESS

- 1 – CEMENT BASED AND WHITE
STONE AND CONCRETE ADHESIVE
FORMULATION AND PRODUCTION PROCESS – 1**

- 2 – CEMENT BASED AND WHITE
STONE AND CONCRETE ADHESIVE
FORMULATION AND PRODUCTION PROCESS – 2**

- 3 – CEMENT BASED AND WHITE
STONE AND CONCRETE ADHESIVE
FORMULATION AND PRODUCTION PROCESS – 3**

**WHITE
STONE AND CONCRETE ADHESIVE
PRODUCTION PROCESS – I**

NO	INGREDIENTS		W/W
1	PORLAND WHITE CEMENT (42,5 r)		427
2	SILICA SAND (100 – 300 MICRON)		570
3	METHYL CELLULOSE (MC) (45.000)		3
	TOTAL		1000 KG

PROCESS:In the above ingredients are solid and powder. So, Charge all ingredients in the mixing tank. Start to mix. Continue to stirr until mixture is homogenous. Homogenous is enough. Process is completed.

NOTE: Amount of ingredients used above formulation can be changed depending condition of market.

**WHITE
STONE AND CONCRETE ADHESIVE
PRODUCTION PROCESS – 2**

NO	INGREDIENTS		W/W
1	PORLAND WHITE CEMENT (42,5 r)		410
2	SILICA SAND (100 – 300 MICRON)		587.5
3	METHYL CELLULOSE (MC) (45.000)		2.5
	TOTAL		1000 KG

PROCESS:In the above ingredients are solid and powder. So, Charge all ingredients in the mixing tank. Start to mix. Continue to stirr until mixture is homogenous. Homogenous is enough. Process is completed.

NOTE: Amount of ingredients used above formulation can be changed depending condition of market.

**WHITE
STONE AND CONCRETE ADHESIVE
PRODUCTION PROCESS – 3**

NO	INGREDIENTS	W/W
1	PORLAND WHITE CEMENT (42,5 r)	350
2	SILICA SAND (100 – 300 MICRON)	647
	STARCH ETHER	1
3	METHYL CELLULOSE (MC) (45.000)	2
	TOTAL	1000 KG

PROCESS:In the above ingredients are solid and powder. So, Charge all ingredients in the mixing tank. Start to mix. Continue to stirr until mixture is homogenous. Homogenous is enough. Process is completed.

NOTE: Amount of ingredients used above formulation can be changed depending condition of market.